

Scar-Guard® Composite Mechanical Protection for Directionally Drilled Pipelines

The patented Scar-Guard® line of products is designed to protect field joint and mainline coatings from the mechanical stresses and scarring associated with horizontal directional drilling (HDD), boring and micro-tunneling of pipelines. **Scar-Guard®** is a composite abrasion resistant overcoat comprised of fiberglass cloth and pre-impregnated flexible resin that is activated by water and cured within minutes. This sacrificial outer laminate system protects pre-approved anticorrosion field joint coatings and mainline coatings such as FBE, liquid epoxies, shrink sleeves, and tapes. The **Scar-Guard®** line of products minimizes the need for costly repairs after pull back, and provides robust protection of the underlying pipeline coating. U.S. Patent #8522827

Bury, Bore or Drill with Confidence

- Provides unparalleled protection against impact, abrasion, gouge, punctures and tears that may result from directional drilling, rough handling, native backfills or severe in-service conditions

Cure Options for any Environment

- Fast cure, slow cure, UV-Curable, UV-Resistant – all available options to suit a wide range of project cycle time requirements and construction conditions

Non-Shielding

- Suggested voltages for high-spark voltage testing as per NACE SP0188 pass through Scar-Guard® to ensure the anticorrosion coating can be tested for integrity after pull-through and protected for the lifetime of the asset.

Fast, Easy Installation

- Scar-Guard® products are simply wrapped onto the existing coatings surface and activated by water. Pre-impregnated moisture cured polyurethane resin means - no field mixing or saturation required!



Applications



Onshore Pipelines



Offshore Pipelines



Abrasion Resistant
Overcoat (ARO)



HDD, Drilling and Boring



Girth-Weld Joints



Mainline Coating Protection

Scar-Guard®

Composite Mechanical Protection for Directionally Drilled Pipelines

Properties	Test Method	Scar-Guard®
Total Thickness	SSPC-PA-2	68 mils
Thickness per Layer	SSPC-PA-2	34 mils
Density	ASTM D792	n/a
Colour	Visual	Grey
Resin Type	Per Manufacturer	Polyurethane
Impact Resistance	ASTM G14-04	48 Joules
Gouge Resistance	CSA Z245.20.10	16 mils at 50 kg
Abrasion Resistance	ASTM D4060	1667 cycles/mil
Compressive Strength	ASTM D695	27,182 psi
Tensile Strength	ASTM D638	n/a
Dielectric Strength	ASTM D149	263 V/mil
Adhesion to existing coating (FBE)	ISO 21809-3 Annex C	Rating 1
Hardness (Shore D)	ASTM D2240	78 @ < 75°F
Cure Schedule*		
Pot Life (Gel Time)	100-gram resin mass	12 min
Hard Dry Time (Shore D > 70)	ASTM D2240	30 min

*Cure times were tested at an ambient temperature of 24°C (75°F).

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.



Canusa-CPS A division of Shawcor Ltd.

Head Office

25 Bethridge Road
Toronto, ON, Canada M9W 1M7
Tel: +1 416 743 7111
Fax: +1 416 743 5927

Canada

Dome Tower St. 2200, 333-7th Avenue SW
Calgary, AB, Canada T2P 2Z1
Tel: +1 403 218 8207
Fax: +1 403 264 3649

Americas

5875 N. Sam Houston Pkwy W., Suite 200
Houston, TX, USA 77086
Tel: +1 281 886 2350
Fax: +1 281 886 2353

Middle East

Plot # 37-WR43, Sector no.: ICAD III
Musaffah South, PO Box 2621
Abu Dhabi, The United Arab Emirates
Tel: +971 2 204 9800

Europe, Africa & Russia

Dellaertweg 9-E, Gebouw "Le Carrefour"
2316 WZ Leiden, The Netherlands (NL)
Tel: +31 71 80 802 70
Fax: +31 71 80 802 71

Asia-Pacific

101 Thomson Road, #11-03 United Square
307591 Singapore
Tel: +65 6749 8918
Fax: +65 6749 8919

Quality Management system registered to ISO 9001

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS_Scar-Guard_rev011