

DDX

Advanced girth-weld protection for pipes used in directionally drilled applications

The DDX - Directional Drilling Kit is a high performance system designed to protect welded joints on PP, PE and FBE coated pipelines in directional drilling applications. This system offers unmatched installation simplicity while delivering exceptional protection at the joints during and after the tough conditions associated with HDD activities.

Layers of Protection

- Force-cured epoxy is applied directly to steel for maximum corrosion protection
- Primary sleeve composed of high shear strength adhesive and HDPE heat shrinkable backing provides both corrosion and mechanical protection across the joints
- The secondary sleeve provides additional mechanical protection to the leading edge of the primary sleeve during pull-through operations

Gouge and Abrasion Resistance

- Designed to mitigate the effect of forces associated with directional drilling
- Highly resistant to the effects of soil stresses and pipe movements

Performance Meets Productivity

- Low preheat temperatures and straightforward application steps reduce cycle times and improve productivity
- Simple and forgiving installation results in improved reliability and quality of every joint



Applications



Oil & Gas



Water Pipelines



Directional Drilling



Girth-Weld Joints





Advanced girth-weld protection for pipes used in directionally drilled applications

Sleeve Operating Characteristics	Test Method	Typical Values
Pipeline Operating Temp.		Up to 70°C (158°F)
Minimum Installation Temp.		70°C (158°F)*
Main Line Coating Compatibility		PE, PP & FBE
Adhesive Properties		
Softening Point	ASTM E28	100°C
Lap Shear @ 23°C	EN12068	> 250 N/cm ²
Lap Shear @ 60°C	EN12068	> 35 N/cm ²
Backing Properties		
Tensile Strength	ASTM D638	22 MPa
Elongation	ASTM D638	600%
Hardness	ASTM D2240	55 Shore D
Volume Resistivity	ASTM D257	10 ¹⁷ ohm-cm
Abrasion Resistance	ASTM D4060	6 mg
Bursting Strength	DIN 30672	> 2200 N
Sleeve Properties		
Adhesion Strength @ 23°C	EN 12068	> 125 N/cm
Adhesion Strength @ 60°C	EN 12068	> 15 N/cm
Impact Resistance	EN 12068	> 30 J
Indentation Resistance	EN 12068	Pass
Cathodic Disbondment @ 23°C, 28 days	EN 12068	< 3 mm rad
Cathodic Disbondment @ 65°C, 48 hours	EN 12068	< 3 mm rad
Microbiological Resistance	ASTM G21	Pass
Soil Stress Resistance	EN 489:2009	Pass
Gouge Resistance [†]	CSA Z245.21	0.5 mm
Low Temp. Flexibility	ASTM D2671-C	> -32°C
Total System Thickness	Supplied	Typical Applied
Standard Product	2.8 mm	3.0 mm

(Custom project thickness available. Consult with your local Canusa Representative.)

* Indicated minimum installation temperature is for typical 3-layer systems. Please refer to the appropriate DDX install guide for the minimum installation temperature of a typical 2-layer system.

[†] Average gouge depth. Test method modified for field-applied 2-layer and 3-layer PE coating systems.

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.



Canada

SFL Canusa Canada
333 Bay Street, Suite 2400
Toronto ON M5H 2T6, Canada

info@canusacps.com

USA

3813A Helios Way, Suite 900
Pflugerville, TX 78660

info@canusacps.com

Europe

Elskensakker 8
5571 SK Bergeijk
The Netherlands (NL)

Tel: +31 497 54 25 27

Middle East

Plot # 37-WR43, Sector no.: ICAD III
Musaffah South, PO Box 2621
Abu Dhabi, United Arab Emirates

Tel: +971 (2) 204 9800

Quality Management
system registered to
ISO 9001

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS_DDX_rev022